



**BCC PRODUCTS, INC.**

**BLEHM PLASTICS**

FAST CAST – EPOXIES – ADHESIVES - POLYSULFIDES - URETHANES – POLYESTER PASTES – TOOLING BOARDS – RELEASE AGENTS – SILICONES

## URETHANE ADHESIVE

(Brown)

**DP-11-88**

Urethane

DP-11-88 is a medium viscosity quick setting easy to use urethane adhesive. This system was specifically designed to bond together the MB2001/MB3000 Model/Tooling Board to create desired dimensions in length, width, and height. DP-11-88 offers a working life of 10 to 12 minutes in 1/4 pound mass, and 20 + minutes in a 1/16 inch film.

### Working Properties

Mix Ratio (by weight)	1 to 1
Viscosity (ASTM-D-2393)	
Part A	3,000 cps
Part B	4,500 cps
Mixed (1 Minute)	3,750 cps
Working Life (1/2 lb. mass) 75E F	10 - 12 minutes
Gel Time (ASTM-D-2471)	12 - 14 minutes
Demold Time (Adhesive) 75EF	8 to 12 hours

### Physical Properties

Specific Gravity, Cured (ASTM-D-792-66)	0.78
Weight/cu.in. (lbs.)	0.028
cu. in./lb (in.)	35.24
Hardness, Shore D (ASTM-D-2240)	62
Tensile Strength (ASTM-D-638)	2,160 psi
Flexural Strength (ASTM-D-790)	3,400 psi
Flexural Modulus (ASTM-D-790)	168,000 psi
Compressive Strength (ASTM-D-695)	2,775 psi
Impact Resistance	2.41 ft. lbs./in.
Heat Distortion (EF) (ASTM-D-648-56)	145E F
Lineal Shrinkage (ASTM-D-2566-69)	.001 in./in.

### URETHANE ADHESIVE

2140 Earlywood Drive, P.O. Box 327, Franklin, IN 46131

Ph (317) 736-4090 Fax (317) 736-4872

Web: [www.bccproducts.com](http://www.bccproducts.com) & [www.blehmplastics.com](http://www.blehmplastics.com)

## DP-11-88

page 2

### Handling Properties

DP-11-88 Urethane Adhesive is a quick-setting, two part casting system which requires careful preparation prior to mixing parts A and B. Because DP-11-88 contains components having very low density, there will be some separation at the surface of the material in its container. Using a paint shaker, jiffy mixer, or mixing spatula, resuspension of the ingredients is easily accomplished. Precaution should be taken to prevent any moisture contamination from containers or utensils. It is recommended that the work area be well ventilated and normal cleanliness and safety rules be observed. Avoid prolonged exposure to vapors and contact with skin.

### Preparation of Mold Surface for Casting Applications

Clean the surface from dust and possible presence of moisture. Apply BC 87 Parting Agent and polish to a uniform high gloss finish (usually 2-3 coats are recommended). For wood surfaces, 2-3 coats of a quality sanding sealer is necessary. For plaster surfaces, seal with PVC sealer to ensure complete absence of moisture. For both wood and plaster surfaces, follow with 2-3 coats of BC 87 Parting Agent.

### Mixing and Pouring for Casting Applications

Pour weighted or measured amounts of Part A & B into a separate dry container by pouring Part A into Part B. Mix with a spatula or mechanical stirrer for 1 minute for quart size batches or 1 1/2 - 2 minutes for gallon batches. Immediately pour mixed resin uninterrupted from a convenient height above the mold cavity to resist air bubble entrapment. Clean your mixing tools by rinsing in an alcohol type solvent. Larger masses (2 feet or more) may be built up with successive pours. Castings may be demolded within 2 to 3 hours but should be properly supported while "green". Under normal conditions, maximum hardness or cure will be achieved in 12-18 hours.

2140 Earlywood Drive, P.O. Box 327, Franklin, IN 46131

Ph (317) 736-4090 Fax (317) 736-4872

Web: [www.bccproducts.com](http://www.bccproducts.com) & [www.blehmplastics.com](http://www.blehmplastics.com)